

Chorzów, 30.09.2022 r.

Technical data sheet

Polystyrene panels EPS 037 ROOF FLOOR STANDARD



DESCRIPTION:

EPS 80 037 ROOF FLOOR STANDARD

Code of designation: EPS EN 13163 T(1)-L(2)-W(2)-S_b(5)-P(5)-BS125-CS(10)80-DS(N)2-DS(70,-)1

The product complies with harmonised standard applicable for this product type: EN 13163:2012+A1:2015 Thermal insulation products for buildings – Factory made expanded polystyrene (EPS) products – Specification.

Panels made with use of polystyrene foaming method and designed for thermal insulation of floors, roofs and flat roofs.

Standard dimensions of panels: 1000 x 500 mm. Customised dimensions on request.

Panel thickness: 10 – 500 mm

Panels can be manufactured with even or finely-milled edges.

USE:

EPS 037 ROOF FLOOR STANDARD polystyrene panels applied in insulations which require shifting of extensive mechanical load, among others:

- insulation of socles in external thermal insulation composite systems ETICS,
- insulation of walls below ground level, with water insulation,
- insulation of floors, attics, converted and unconverted lofts,
- insulation of floors in residential and public utility construction,
- insulation of floors in underfloor heating systems,
- insulations of flat and steep roofs over, under and between transoms,
- core of wall and roof sandwich panels.

Polystyrene panels should be used according to the manufacturer's recommendations, guidelines defined in construction design and rules of the trade which means that investment should be implemented in accordance with any and all legal and technical regulations applicable in the construction industry, while maintaining due diligence and taking advantage of the best professional knowledge. Do not use panels in a direct contact with substances having a destructive effect on EPS polystyrene, e.g. organic solvents (acetone, benzene, nitro), etc.

PACKING, STORAGE, TRANSPORT:

EPS 037 ROOF FLOOR STANDARD polystyrene panels are delivered only in original Manufacturer's packaging. Polystyrene panels should be stored in a manner preventing them against damage, and protected against direct effect of weather conditions (UV radiation) which destructively affect the surface of polystyrene.

Leaving polystyrene for a longer time with no cover can cause tarnish to appear over its surface. In such case before application of panels it is necessary to remove the tarnish by grinding.

Documentation

- Declaration of Performance no. 09/S037_80DP
- Information on EPS safety and operation

PaNELTECH Sp. z o.o.

ul. Michałkowska 24
41-508 CHORZÓW
tel: 32 245 91 41
info@paneltech.pl

NIP: 627 00 12 306
Kapitał zakładowy: 210 000 zł.
Sąd Rejonowy w Katowicach Wydział Gospodarczy KRS Nr: 0000105517
ING Bank Śląski S.A. Oddział Bytom: 10 1050 1230 1000 0002 0000 3721



PANELTECH.PL

PERFORMANCE:

| Essential characteristics for the intended use, for thermal insulation in the construction industry | Declared performance, class or level |
|---|--|
| Dimensional tolerance class: thickness, length, width, rectangularity, flatness | T1 (± 1 mm) L2 (± 2 mm) W2 (± 2 mm) S _b 5 (± 5 mm/1m) P5 (5 mm) |
| Bending strength | BS 125 ≥ 125 kPa |
| Dimensional stability under constant normal laboratory conditions | DS(N)2 ± 0,2 % |
| Dimensional stability under specific conditions – temperature 70 °C, 48 h | DS(70,-)1 ≤ 1 % |
| Compressive stress with 10% relative deformation | CS(10)80 ≥ 80 kPa |
| Declared thermal conductivity coefficient λ _D | 0,037 W/(m K) |
| Thermal resistance R _D | Table 2 |
| Reaction-to-fire class | E |

Table no. 2 Summary of thermal resistance as a function of thickness

| | | | | | | | | | | | | | | | |
|--|------|------|------|------|------|------|------|------|------|------|------|------|------|------|------|
| Thickness, d _N [mm] | 10 | 20 | 30 | 40 | 50 | 60 | 70 | 80 | 90 | 100 | 110 | 120 | 130 | 140 | 150 |
| Thermal resistance R _D [m ² K/W] | 0,25 | 0,50 | 0,80 | 1,05 | 1,35 | 1,60 | 1,85 | 2,15 | 2,40 | 2,70 | 2,95 | 3,20 | 3,50 | 3,75 | 4,05 |
| Thickness, d _N [mm] | 160 | 170 | 180 | 190 | 200 | 210 | 220 | 230 | 240 | 250 | 260 | 270 | 280 | 290 | 300 |
| Thermal resistance R _D [m ² K/W] | 4,30 | 4,55 | 4,85 | 5,10 | 5,40 | 5,65 | 5,90 | 6,20 | 6,45 | 6,75 | 7,00 | 7,25 | 7,55 | 7,80 | 8,10 |

Standard dimensions of panels: 1000 x 500 mm.

Table no. 3 Packaging

| | | | | | | | | | | | | | | | |
|---|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| PANEL THICKNESS (m) | 0,01 | 0,02 | 0,03 | 0,04 | 0,05 | 0,06 | 0,07 | 0,08 | 0,09 | 0,10 | 0,11 | 0,12 | 0,13 | 0,14 | 0,15 |
| PACKAGE VOLUME (m ³) even edges | 0,300 | 0,300 | 0,300 | 0,300 | 0,300 | 0,300 | 0,280 | 0,280 | 0,270 | 0,300 | 0,275 | 0,300 | 0,260 | 0,280 | 0,300 |
| PACKAGE VOLUME (m ³) finely-milled edges | - | - | - | - | 0,282 | 0,282 | 0,263 | 0,263 | 0,254 | 0,282 | 0,259 | 0,282 | 0,245 | 0,263 | 0,282 |
| PANEL AREA (m ²) even edges | 30,00 | 15,00 | 10,00 | 7,50 | 6,00 | 5,00 | 4,00 | 3,50 | 3,00 | 3,00 | 2,50 | 2,50 | 2,00 | 2,00 | 2,00 |
| PANEL AREA (m ²) finely-milled edges | - | - | - | - | 5,64 | 4,70 | 3,76 | 3,29 | 2,82 | 2,82 | 2,35 | 2,35 | 1,88 | 1,88 | 1,88 |
| NUMBER OF PANELS IN PACKAGE (pcs) | 60 | 30 | 20 | 15 | 12 | 10 | 8 | 7 | 6 | 6 | 5 | 5 | 4 | 4 | 4 |
| PANEL THICKNESS (m) | 0,16 | 0,17 | 0,18 | 0,19 | 0,20 | 0,21 | 0,22 | 0,23 | 0,24 | 0,25 | 0,26 | 0,27 | 0,28 | 0,29 | 0,30 |
| PACKAGE VOLUME (m ³) even edges | 0,320 | 0,255 | 0,270 | 0,290 | 0,300 | 0,315 | 0,220 | 0,230 | 0,240 | 0,250 | 0,260 | 0,270 | 0,280 | 0,290 | 0,300 |
| PACKAGE VOLUME (m ³) finely-milled edges | 0,301 | 0,240 | 0,254 | 0,273 | 0,282 | 0,296 | 0,207 | 0,216 | 0,226 | 0,235 | 0,245 | 0,254 | 0,263 | 0,273 | 0,282 |
| PANEL AREA (m ²) even edges | 2,00 | 1,50 | 1,50 | 1,50 | 1,50 | 1,50 | 1,00 | 1,00 | 1,00 | 1,00 | 1,00 | 1,00 | 1,00 | 1,00 | 1,00 |
| PANEL AREA (m ²) finely-milled edges | 1,88 | 1,41 | 1,41 | 1,41 | 1,41 | 1,41 | 0,94 | 0,94 | 0,94 | 0,94 | 0,94 | 0,94 | 0,94 | 0,94 | 0,94 |
| NUMBER OF PANELS IN PACKAGE (pcs) | 4 | 3 | 3 | 3 | 3 | 3 | 2 | 2 | 2 | 2 | 2 | 2 | 2 | 2 | 2 |

